



## POLY-PLUS CURTAIN - CLEAR DATA SHEET

Count: 10 x 10 tapes/inch

Weight: 4.4 ounces per square yard (136 grams)

Tensile Strength: Warp - 125 lbs. ASTM D751  
(Meth. A) Weft - 100 lbs (Grab Method)

Tear Strength: Warp - 40 lbs. ASTM D4533  
(Meth. B) Weft - 30 lbs. (Tongue Method)

Mullen Burst: 250 p.s.i. ASTM D751

Coating Thickness: 1.5 mil average

Overall Thickness: 7.5 mil average

Scrim Type: Clear Tapes, UV stabilized

Color: Clear (Black, Black/White, Black/Silver &  
Blue Available)

Accelerated More than 80% strength ASTM G53-84  
Weathering/U.V.: retention after 2000 hours  
(Q.U.V. [A-340 Lamps] 8 hrs. U.V. @ 60 deg C./4 hrs condensation @  
50 deg. C)

Width: Up to 144 inches

THESE VALUES ARE TYPICAL DATA AND ARE NOT INTENDED AS LIMITING SPECIFICATIONS.

**WARRANTY:** All AMT Poly-Plus curtain materials carry a three (3) year prorated warranty for deterioration and/or manufacturers defects only. The basis of failure is a 50% reduction in tear strength or original fabric. The manufacturer's sole obligation is to replace or repair the defective material per warranty terms. Warranty excludes any and all labor and/or transportation costs. There is no warranty, expressed or implied, as to the percentage of opacity in black, black/white or black/silver material. We do not warrant against pin-hole light spots in black fabrics.

DS 04/97